



KEMICA COATINGS  
*Reinventing coatings*

# SOUPLETHANE 5 KITCHEN

Installation procedure

KITCHEN RENOVATION



bio-based



sustainable



eco-friendly

---

**100%**

waterproofing  
anticorrosion  
non flammable  
antifouling  
antibacterial

---

**0%**

solvent  
toxicity  
VOC  
BPA

# SOUPLETHANE 5 KITCHEN

Solvent-free resin range  
inspired by nature



biosourcé



durable



écologique

## INSTALLATION PROCEDURE

### 1 - Removal of the old coating

Tiling, rubble removal  
and mechanical sanding  
incl. dust removal



## KITCHEN RENOVATION



# SOUPLETHANE 5 KITCHEN

Solvent-free resin range  
inspired by nature



## INSTALLATION PROCEDURE

### 2- Singular Point Treatment

upstands, laying of a **KEMTEX** multidirectional fiber

280gr/m<sup>2</sup>, width 12 cm

Junction of floors and insulated panels, bonded with **SOUPLETHANE 5/6 PUTTY**

Siphon recovery, **SOUPLETHANE 5/6 PUTTY**

## KITCHEN RENOVATION



# SOUPLETHANE 5 KITCHEN

Solvent-free resin range  
inspired by nature



biosourcé



durable



écologique

## INSTALLATION PROCEDURE

### 3 -Primer

Application of the **PU AQUEUX** primer, 150 gr/m<sup>2</sup>

## KITCHEN RENOVATION





# SOUPLETHANE 5 KITCHEN

Solvent-free resin range  
inspired by nature

## INSTALLATION PROCEDURE




biosourcé



durable



écologique



## KITCHEN RENOVATION

### 4 - Full floor canvas, multidirectional fiberglass 350 gr/m<sup>2</sup>

Glued with SOUPLETHANE 5 resin, then grinding of the entire current surface after the resin has fully cured



# SOUPLETHANE 5 KITCHEN

Solvent-free resin range  
inspired by nature

## INSTALLATION PROCEDURE

### 5 - Waterproofing of the current surface

Application of a layer of **SOUPLETHANE 5** with a notched spatula, consumption 2,6 kg/m<sup>2</sup> and sprinkling of quartz aggregates (0.4/0.8 mm) to refusal

### 6 - Top coat

After grinding the mineral aggregates and careful suction Application with a roller of **SOUPLETHANE 5 COR** at a rate of 600 g/m<sup>2</sup>




biosourcé



durable



écologique





**Discover the entire range of SOUPLETHANE solvent-free resins as well as :**

- Our innovations and news
- Our qualifications and performance
- Our recommendations and solutions
- Our implementations and application techniques

On our website : [www.kemica-coatings.com](http://www.kemica-coatings.com)



PRESENT IN FRANCE AND INTERNATIONALLY, KEMICA COATINGS offers delivery solutions adapted to its customers' practices.



Z.A. du Bois Gueslin F-28630 Mignières - France  
Tél. : +33 (0)237 26 3356  
e-mail : [contact@kemica-coatings.com](mailto:contact@kemica-coatings.com)